




Accura[®] 25 plastic

for use with solid-state stereolithography (SLA[®]) systems

Simulate the properties and aesthetics of polypropylene with this accurate and flexible material.



APPLICATIONS

- Functional components for assemblies and mock-ups for:
 - Automotive styling parts — trim, fascia, and other components
 - Consumer electronic components
 - Toys
 - Snap fit assemblies
- Master patterns for RTV/silicone molding
- Replace CNC machining of polypropylene to produce short-run plastic parts
- Simulate injection molded parts
- Concept and marketing models

FEATURES

- Look and feel of molded polypropylene
- High flexibility with excellent shape retention
- Outstanding feature resolution and accuracy
- High production speed
- Fully developed and tested build styles

BENEFITS

- Increased market opportunities for models
- Reliable and robust functional prototypes
- Suitable for master patterns
- More parts and better system utilization
- Easy to use with no user R&D

Accura 25 plastic

For use with solid-state stereolithography (SLA) systems

TECHNICAL DATA

Liquid Material

MEASUREMENT	CONDITION	VALUE:
Appearance		White
Liquid Density	@ 25 °C (77 °F)	1.14 g/cm ³
Solid Density	@ 25 °C (77 °F)	1.19 g/cm ³
Viscosity	@ 30 °C (86 °F)	250 cps
Penetration Depth (Dp)*		4.2 mils
Critical Exposure (Ec)*		10.5 mJ/cm ²
Tested Build Styles		FAST™, EXACT™, Exact HR

Post-Cured Material

MEASUREMENT	CONDITION	VALUE:
Tensile Strength	ASTM D 638	38 MPa (5,450 - 5,570 PSI)
Tensile Modulus	ASTM D 638	1,590 - 1,660 MPa (230 - 240 KSI)
Elongation at Break (%)	ASTM D 638	13 - 20 %
Flexural Strength	ASTM D 790	55 - 58 MPa (7,960 - 8,410 PSI)
Flexural Modulus	ASTM D 790	1,380 - 1,660 MPa (200 - 240 KSI)
Impact Strength (Notched Izod)	ASTM D 256	19-24 J/m (0.4 ft- lb/in)
Heat Deflection Temperature	ASTM D 648 @ 66 PSI @ 264 PSI	58 - 63 °C (136 - 145 °F) 51 - 55 °C (124 - 131 °F)
Hardness, Shore D		80
Co-efficient of Thermal Expansion	ASTM E 831-93 TMA (T<Tg, 0 - 20°C) TMA (T>Tg, 90 - 150°C)	107 x 10 ⁻⁶ m/m °C 151 x 10 ⁻⁶ m/m °C
Glass Transition (Tg)	DMA, E''	60 °C (140 °F)

· Dp/Ec values are the same on all systems.



3D Systems Corporation
26081 Avenue Hall
Valencia, CA 91355 U.S.A.

661.295.5600, ext. 2882
Toll-free: 888.337.9786
Fax: 661.294.8406

moreinfo@3dsystems.com
www.3dsystems.com
Nasdaq: TDSC

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2005 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. The 3D logo is a trademark, and Accura and SLA are registered trademarks of 3D Systems, Inc.